

Water line measurement for bottom painting



Hio maalattavan alueen pinta karheaksi santapaperilla karkeus 80 - 120. Maalaa alue hard racing eliönestomaalilla kaksi kerrosta. ABS-muovi ei tarvitse primer maalia.

Sand painting area by sand paper roughness 80 - 120. Paint bottom with hard racing paint. Paint two layers. ABS-plastic does not need primer paint.

Malli	A cm	B cm
Tender / Baby Fun	35	40
Sunny	35	60
385	35	60
390	35	60
400	25	77
440	35	75
Saiman	45	75
More Fun	30	70
Sea Fun	35	70
Sea Fun C	30	70
4110	35	75
445 / 445 C	34	88
450 / 450 C / 450 CC	32	86
Nordic	42	105
Nordic C	42	105
475 Open CC	31	78
475 Open FC	31	78
475 Twin C	31	78
475 BR	31	78
480 BR / Sport	31	78
480 TC	31	78
480 Cabin	30	71